

Microglass filter media

HEPA 99,99

HEPH1403

Application

Air Filtration

Characteristics:

This filter media is manufactured from an advanced blend of borosilicate microglass fibers and acrylic resins.

Suitable for deep-pleat and mini-pleat applications

HEPH1403

Physical properties	Units	MIN	STD	MAX	Test Method
					CONDITIONS 23 ± 2 °C - 50% ± 5 U.R
Grammage	gr/m ²	72,0	75,0	78,0	TAPPI T410
	lb/3000ft ²	44,2	46,1	47,9	
Thickness	mm	0,400	0,450	0,500	Internal Method
	mils	15,7	17,7	19,7	
Efficiency	%	99,990			@ 0,3µ 5.32 cm/sec
Pressure Drop	mm H ₂ O		32,5	34,5	@ 5.32 cm/sec
	Pa		319	338	
Tensile MD	kN/m	0,80	1,20		TAPPI T494
	gr/inch.	2,044	3,067		
	Kg/15 mm	1,22	1,84		
Tensile MD After Fold	kN/m	0,57	0,80		Internal Method
	gr/inch.	1,457	2,044		
	Kg/15 mm	0,87	1,22		
Elongation MD	%	1,0	1,2		TAPPI T494
Stiffness MD	mg	900	1000		TAPPI T543
Water Repellency	mm	400	700		Mil Std 282 (Q-101)
	inches	16	28		
Loss of Ignition	%		6,0	8,0	† 30' - T 520 °C
Yield	m ² /Kg	13,9	13,3	12,8	Internal Method
	ft ² /lb	67,8	65,1	62,6	

The above data are referring to the flat sheet filter media. Final filter characteristics will depend on parameters and filter design used.

Issue date: 05-05-2008 - Version 0

Contact office

Ahlstrom Turin S.p.A.
 Fabriano Plant
 Loc. Campoginepro
 Fraz. Gaville
 I-60041 Sassoferrato, AN, Italy
 T: + 39 0732 9127
 F: + 39 0732 970464

www.ahlstrom.com

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom deems appropriate. Refer to www.ahlstrom.com for contact information.